

# Avery Dennison® W-6200

High Intensity Grade Reflective Sheeting  
 Pre-Striped Barricade  
 Pressure Sensitive Adhesive for Wood and Aluminum

Data Bulletin # W-6200

Issued: 05/01

Updated: 05/02

## Description:

Avery Dennison W-6200 High Intensity Grade Pre-Striped Reflective sheeting for barricades is a high-quality, durable, micro-prismatic retroreflective material. This reflective sheeting is designed specifically for use on most properly prepared wood surfaces used for traffic control devices. Meets all applicable requirements for for Type III retroreflective sheeting as set forth in ASTM D 4956.

## Construction:

<b>Face Film:</b>	High gloss with 4" or 6" diagonal stripes
<b>Adhesive</b>	Permanent Pressure Sensitive (Class 1).
<b>Liner:</b>	Film

## Photometric Performance:

Type III values per ASTM D 4956. Minimum Coefficient of Retroreflection ( $R_A$ ) ( $cd / lx / m^2$ )

Observation Angle	Entrance Angle	White	Orange
0.2°	-4°	250	100
	30°	150	60
0.5°	-4°	95	30
	30	65	25

## Colors & Specification Limits (Daytime)<sup>A</sup>:

Color	1		2		3		4		Luminance (Y%)	
	x	y	x	y	x	y	x	y	Min	Max
White	0.303	0.300	0.368	0.366	0.340	0.393	0.274	0.329	27	--
Orange	0.558	0.352	0.636	0.364	0.570	0.429	0.506	0.404	14	30

<sup>A</sup>The four pairs of chromaticity coordinates determine the acceptable color in terms of the CIE 1931 Standard Colorimetric System measured with Standard Illuminant D65.

## Other Specifications:

Consult your Avery Dennison Representative for information concerning additional world-wide specifications.

Avery Dennison® W-6200 continued...

*Physical Properties:*

<b>Outdoor Durability</b>	Avery Dennison W-6200 sheeting has a 3 year durability when properly processed and applied.
<b>Minimum Surface &amp; Ambient Air Application Temperature</b>	65°F (18°C) when applied with a squeeze roll applicator.
<b>Application Surface</b>	Recommended for flat surfaces only. Smooth, dry wood surfaces must be sealed with a compatible paint or primer prior to application, following all applicable paint/primer-drying instructions. Use of Aluminum or MDO or HDO plywood is preferred. Always pretest your specific substrate prior to actual application. Note: Use of wet method of application is not recommended for W-6200 reflective sheeting.
<b>Service Temperature Range</b>	-40°F to 180°F (-40°C to 82°C)
<b>Typical Film Caliper (w/adhesive)</b>	18 to 19 mils
<b>Shelf Life</b>	One year when stored at the following temperature and conditions 68° - 77°F (20° - 25°C) and 50% ± 5%± R.H.
<b>Other Tests:</b>	W-6200 meets all other requirements set forth in ASTM D 4956 including Shrinkage, Flexibility, Liner removal, Adhesion, Impact resistance, Specular gloss and Outdoor weathering.

*Application & Conversion Information:*

The following Avery Dennison literature will provide complete information to the user for proper application, storage, and other requirements and is available from your Avery Dennison representative, from the Avery Dennison web-site [www.reflectives.averydennison.com](http://www.reflectives.averydennison.com), or on request:

<b>Instructional Bulletins:</b>	
Sheeting Care & Handling	#8.00
Substrate Requirements	#8.01
Application Techniques for PS Sheeting	#8.10
Printing	Not designed For printing applications

<b>Stripe Pattern:</b>	
W-6242	4 inch left, 45° diagonal stripes
W-6243	4 inch right, 45° diagonal stripes
W-6244	6 inch left, 45° diagonal stripes
W-6245	6 inch right, 45° diagonal stripes

Avery Dennison® W-6200 continued...

**Warranty:**

*WARRANTY: All statements, technical information and recommendations about Avery Dennison products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that Purchaser has independently determined the suitability of such products for its purposes. Avery Dennison products are warranted to be free from defects in material and workmanship for either one year (or the period stated on the specific product information literature in effect at time of delivery, if longer) from date of shipment if said product is properly stored and applied. It is expressly agreed and understood that Avery Dennison's sole obligation and Purchaser's exclusive remedy under this warranty, under any other warranty, express or implied, or otherwise, shall be limited to repair or replacement of defective product without charge at Avery Dennison's plant or at the location of product (at Avery Dennison's election), or in the event replacement or repairs is not commercially practical, to Avery Dennison's issuing Purchaser a credit reasonable in light of the defect in the product.*

*Avery Dennison's liability for defective products shall not exceed the purchase price paid therefore by Purchaser and in no event shall Avery Dennison be responsible for any incidental or consequential damages whether foreseeable or not, caused by defects in such product, whether such damage occurs or is discovered before or after replacement or credit, and whether or not such damage is caused by Avery Dennison's negligence.*

**NO EXPRESS WARRANTIES AND NO IMPLIED WARRANTIES, WHETHER OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR USE, OR OTHERWISE (EXCEPT AS TO TITLE), OTHER THAN THOSE EXPRESSLY SET FORTH ABOVE WHICH ARE MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND MANUALLY SIGNED BY AN OFFICER OF AVERY DENNISON.**

Avery Dennison , 6565 W. Howard, Niles, IL 60714, USA, 1-800-327-5917, [www.reflectives.averydennison.com](http://www.reflectives.averydennison.com)